

**AMENDMENTS TO THE CLAIMS**

1. (Original) A rubber material composition comprising:  
carboxylated acrylonitrile-butadiene rubber.
2. (Original) The rubber material composition as set forth in claim 1, further comprising:  
20 to 90 wt parts of carbon black for 100 wt parts of said carboxylated acrylonitrile-butadiene rubber.
3. (Original) The rubber material composition as set forth in claim 1, further comprising:  
10 to 60 wt parts of polyolefin based resin for 100 wt parts of said carboxylated acrylonitrile-butadiene rubber.
- 4-6. (Canceled)
7. (New) A rubber material composition consisting essentially of:  
carboxylated acrylonitrile-butadiene rubber; and  
10 to 60 wt parts of polyolefin resin for 100 wt parts of said carboxylated acrylonitrile-butadiene rubber,  
wherein the polyolefin resin is selected from the group consisting of carboxylic modified polyethylene and carboxylic modified polypropylene.
8. (New) A rubber material composition comprising:  
carboxylated acrylonitrile-butadiene rubber; and  
10 to 60 wt parts of polyolefin based resin for 100 wt parts of said carboxylated acrylonitrile-butadiene rubber,  
wherein the polyolefin based resin is selected from the group consisting of carboxylic modified polyethylene and carboxylic modified polypropylene.